

JPL SPRAYTEX

JPL TERRASHIELD TEXTURE SPRAY

Terrashield Texture Spray is a sprayable decorative version of Terrashield Fine, applied with a multi-nozzle gun to create finishes like orange-peel, splatter, and stucco. Overcoated with JPL emulsions, it delivers a durable, premium façade finish.



TECHNICAL ADVANTAGES

- Sprayable crack bridging texture — no on-site cement-mix tinting
- Multi-nozzle gun: same product, four standard architectural finishes
- Carries Terrashield Fine chemistry — Class A fire, anti-fungal, water-resistant
- Polymer-bound granules — does not chalk, debond or detach over time
- Compatible with full JPL paint range for colour & sheen specification
- Bridges hairline cracks; absorbs thermal / structural movement
- Faster site rate vs. trowel-applied stucco; lower waste and rebound
- Matches the BOQ-ready 8T-2699 / 8D-2703 reference shades from Krisumi

PACKAGE AVAILABLE

Shelf Life - 12 Months



30 Kg Bucket

APPLICATION PROCEDURE

- Apply 1–2 coats of Terrashield Fine (2 × 1 mm) and allow to dry per TF TDS.
- Spray 1 coat of tinted Terrashield Texture Spray through the multi-nozzle gun in the chosen finish (orange-peel, splatter, knock-down, stucco).
- After \geq 96 hours, apply 1 coat of JPL emulsion (Exto / Weathertouch / Spade / Into / Premium) for colour, plus optional Clear Emulsion for shine and sheen.

WHY SPECIFY

- Designer textured façade in a single crack bridging system
- Multi-nozzle spray gun delivers four interchangeable finishes
- Carries Terrashield Fine's crack bridging, fire-retardant, anti-fungal performance
- Eliminates rendered-stucco failure modes — no river sand, no cement-mix shrinkage

KEY SPECIFICATIONS

- **Form** - Coarsened crack bridging polymer paste (paste; ready to spray)
- **Application** - Multi-nozzle texture spray gun (4 – 8 mm nozzle range)
- **Base Build-Up** - 1–2 coats Terrashield Fine, then 1 sprayed texture coat
- **Texture Coat** - 1.5 – 4 mm depending on nozzle / finish chosen
- **Finishes** - Orange-peel · Splatter · · Stucco Knock-down
- **Topcoat** - JPL emulsion (tinted) + optional clear sheen
- **Paint Ready** - In - 96 hours after texture coat
- **Pack Size** - 20 kg pail (texture grade) / 5 kg trial

APPLICATIONS

- External Mivan, RCC and AAC façades requiring designer texture
- Premium residential and commercial facades (towers, clubhouses, lobby drops)
- Boundary walls, parapets and soffits requiring crack bridging crack protection
- Feature walls / accent panels in interior atriums and double-height lobbies
- Refurbishment of existing painted façades — applied over sound, primed substrates

NABL TEST RESULTS

As per Terrashield Fine Base

| | |
|------------------|-------------------------------|
| Class 1 or A | Fire Retardant Surface rating |
| 3.2 MPA | Compressive Strength |
| 5.8 MPA | Tensile Strength |
| 1.9 MPA | Flexural Strength |
| 24.3% Absorption | after submerged for 24hrs. |
| 1.0 MPA | Pull of Strength |

COVERAGE

| MAX. THICKNESS | AREA IN SQ.FT / 20KG |
|----------------|----------------------|
| 1.5 – 2 mm | 450 |

TECHNICAL DATA

| | |
|--------------------------|---|
| Base build-up | Terrashield Fine, 2 × 1 mm |
| Texture coat thickness | 1.5–4 mm (nozzle dependent) |
| Spray pressure | 4–6 bar (compressor-fed gun) |
| Nozzle aperture | 4 / 6 / 8 mm interchangeable |
| Finishes | Orange-peel, Splatter, Knock-down, Stucco |
| Recoat (texture → paint) | 96 hours |